



CHLORINATED SWIMMING POOL PAINT

PRODUCT DATA SHEET

A chlorinated rubber based swimming pool paint especially formulated for coating the interior of cement based swimming pools.

CHLORINATED SWIMMING POOL PAINT is resistant to water and to the standard chemicals used for swimming pool water treatment.

USAGE

- For painting concrete and plastered swimming pools.

Note : Much care must be taken in surface preparation and application of the sealer as these steps are essential to ensure good adhesion and to avoid blistering and flaking.

PHYSICAL DATA

- **Product Code** : 1315
- **Finish** : Gloss
- **Colour** : White, Blue
- **Consistency** : Semi - viscous Liquid
- **Specific Gravity** : 1.33 (approx.)
- **Volume Solids** : 35% (approx.)
- **Flash Point** : < 23 °C, closed cup
- **Shelf Life** : 12 months
- **Packing** : 20 L, 5 L, 2 L, 1L, 500 ml

Paints should be stirred before use and occasionally whilst in use.
Contact your supplier for further information

APPLICATION

- **Surface preparation** : See method SP 001. Concrete surfaces should be clean and free of any contaminants. Apply one coat of diluted **CHLORINATED SEALER CLEAR** by roller or brush onto clean, dry surface.
- **Application method** : Apply by roller or brush two to three coats of **CHLORINATED SWIMMING POOL ENAMEL**. Airless spray is also possible.
- **Dilution** : Thin down as required with :-
 - ◇ **SLOW AROMATIC SOLVENT** for brush or roller application and when a longer drying time is desirable.
 - ◇ **AROMATIC SOLVENT** for roller or spray application and when a slower drying time is desirable.
- **Spreading rate / Film thickness** : One litre of **CHLORINATED SWIMMING POOL PAINT** will cover between 7 and 9 m² of surface in one coat ; at this spreading rate the dry film thickness will vary between 50 and 40 microns on a completely smooth, non absorbent surface.
- **Drying time** : Approximately 30 minutes to touch dry, **CHLORINATED SWIMMING POOL PAINT** can be over-coated after approximately 4 hours. The pool can be filled with water after 24 hours of applying the last coat.
- **Cleaning solvent** : **AROMATIC SOLVENT OR SLOW AROMATIC SOLVENT**.
- **Preceding coat** : **CHLORINATED SEALER CLEAR** , diluted to ensure good penetration.
- **Subsequent coat** : Not required.

SAFETY

- **CHLORINATED SWIMMING POOL PAINT** is flammable, keep away from ignition source. Do not smoke whilst using.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.
- A complete Material Safety Data Sheet is available on request.

MAINTENANCE

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.