



# GALVANISED IRON CLEANER

## PRODUCT DATA SHEET

GALVANISED IRON CLEANER is an alcoholic acidic solution .

### USAGE

- For etching and degreasing galvanised iron prior to application of an etch primer.

### PHYSICAL DATA

- **Product Code :** 9602
- **Finish :** N/A
- **Colour :** Clear
- **Consistency :** Liquid
- **Specific Gravity :** 0.87 (approx.)
- **Flash Point :** < 23 °C, closed cup
- **Shelf Life :** 12 months
- **Packing :** 20 L, 5 L, 2 L, 1L

Paints should be stirred before use and occasionally whilst in use.  
Contact your supplier for further information

## APPLICATION

- **Surface preparation** : See method SP 004 for galvanised iron.
- **Application method** : Apply while exerting a slight pressure on the brush, to and fro or in circular movements. Allow to react for 10-15 minutes, wipe with a clean cloth and then clean thoroughly with fresh water.
- **Dilution** : Not required.
- **Spreading rate** : Approximately 15m<sup>2</sup>/litre.
- **Drying time** : Not applicable.
- **Cleaning solvent** : **WATER.**
- **Preceding coat** : Not applicable.
- **Subsequent coat** : **MA 10 PRIMER, TWO PACK ETCH PRIMER, HT 332 METAL PRIMER.**

## SAFETY

- **GALVANISED IRON CLEANER** is a hazardous material and should be used with caution.
- **GALVANISED IRON CLEANER** is flammable, keep away from ignition source. Do not smoke whilst using.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.
- A complete Material Safety Data Sheet is available on request.

## MAINTENANCE

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.