



MAUVILASURE

PRODUCT DATA SHEET

MAUVILASURE is a range of high quality alkyd resin based glossy varnishes for wood, available in clear and in four transparent shades.

MAUVILASURE is a highly flexible varnish formulated to provide maximum flexibility and excellent resistance to cracking and flaking. The clear varnish contains ultra violet absorbers and the tinted versions contain tinters which will absorb ultra-violet light, these will extend the coating life when exposed to sunlight. The thixotropic nature of **MAUVILASURE** provide for great ease of application by brush or roller and prevents spattering. **MAUVILASURE** has excellent flow and levelling properties and dries to a durable washable dry film which enhances the appearance of the wood.

USAGE

- On exterior wood such as beams, balustrades, doors, window frames, garden furniture, wooden structures, etc...
- On interior wood such as beams, panels, doors, window frames, skirtings, decorative objects, etc....
- Do not use **MAUVILASURE** on surfaces which require hard wear and tear properties such as counter tops, tables tops, floors , etc..

PHYSICAL DATA

- **Product Code :** 0859
- **Finish :** Gloss
- **Colour :** Clear, Mahogany, Oak, Sapele, Teak
- **Consistency :** Thixotropic liquid.
- **Specific Gravity :** 0.92 (approx.)
- **Volume Solids :** 45 % (approx.)
- **Flash Point :** 38 ° C (Closed cup)
- **Shelf Life :** 12 months
- **Packing :** 20 L, 5 L, 2 L, 1 L

Paints should be stirred before use and occasionally whilst in use.
Contact your supplier for further information

APPLICATION

- **Surface preparation** : See method SP 002.
- **Application method** : Apply two to three coats by roller or brush onto clean, dry surface.
- **Dilution** : Thin down with **TEST BENZIN** as required. On new wood the first coat should be diluted to ensure good penetration.
- **Spreading rate / Film thickness** : One litre of **MAUVILASURE** will cover between 10 and 15 m² of surface in one coat ; at this spreading rate the dry film thickness will vary between 45 and 30 microns on a completely smooth, non absorbent surface.
- **Drying time** : Approximately 5 hours to touch dry, **MAUVILASURE** can be over-coated after approximately 16 hours.

Note: **MAUVILASURE** has a residual tackiness for over a period of time (up to 30 days depending on ambient conditions) after application. This is a characteristic of the product and is not detrimental to film properties.

- **Cleaning solvent** : **TEST BENZIN**.
- **Preceding coat** : On new surfaces dilute 4 parts of **MAUVILASURE** with 1 part of **TEST BENZIN** for use as a penetrating sealer.
- **Subsequent coat** : Not required.

SAFETY

- **MAUVILASURE** is flammable, keep away from ignition source. Do not smoke whilst using.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.
- A complete Material Safety Data Sheet is available upon request.

MAINTENANCE

To extend the coating life when exposed permanently to direct sunlight, sand down lightly each 24 to 30 months and apply an additional coat.

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

Manufactured and Distributed by:

Mauvilac Industries Ltd

Pailles Road, Pailles, Republic of Mauritius

Tel: (230) 206 4700

Fax: (230) 212 4308

JAN 2002