



VIP SATIN EMULSION

PRODUCT DATA SHEET

A high quality pure acrylic polymer emulsion paint which dries quickly to give an attractive smooth finish.

- **VIP SATIN EMULSION** is on the **MAUVIMATCH** tinting system.

VIP SATIN EMULSION is a decorative and protective coating primarily selected for its exceptional performance, long life and long term economical advantage. It is recommended for decorating and protecting the interior of homes, offices, factories, shops, hotels and other related structures. The outstanding washability and scrubability properties of **VIP SATIN EMULSION** make it ideal as an interior coating. It has proved to be effective in its resistance against fungus in humid areas.

USAGE

- On cement substrates such as plaster, concrete and building blocks.
- On panel wood and ceiling boards.
- On absorbent wall coverings (wall paper, etc.)
- On foamed polystyrene and on flexible synthetic foam.
- On suitably primed interior wood structures.
- Recommended for interior and exterior application.

PHYSICAL DATA

- **Product Code :** 0305
- **Finish :** Mid- Gloss Satin
- **Colour :** Approximately 30 standard pastel colours, white.
- **Consistency :** Medium viscosity liquid
- **Specific Gravity :** 1.23 (approx.)
- **Volume Solids :** 40% (approx.)
- **Flash Point :** Not Applicable
- **Shelf Life :** 12 months
- **Packing :** 20 L, 5 L, 2 L, 1 L

Paints should be stirred before use and occasionally whilst in use.
Contact your supplier for further information.

APPLICATION

- **Surface preparation** : See method SP 001
- **Application method** : Apply two coats by roller or brush onto clean, dry and sealed surface. **VIP SATIN EMULSION** can be applied using airless or low pressure spray equipment.
- **Dilution** : Thin down with water as required; for best results do not exceed the dilution volume ratio of 1 part water to 10 parts paint.
- **Spreading rate / Film thickness** : One litre of **VIP SATIN EMULSION** will cover between 6 and 8 m² of surface in one coat ; at this spreading rate the dry film thickness will vary between 50 and 65 microns on a completely smooth, non absorbent surface.
- **Drying time** : Approximately 30 minutes to touch dry, **VIP SATIN EMULSION** can be over-coated after approximately 4 to 5 hours.
- **Cleaning solvent** : Use water; if necessary add some liquid detergent to warm water.
- **Preceding coat** : Use **CLEAR EMULSION BINDER** or **MAUVILITH SEALER** as a sealer on new cement substrates and on powdery or absorbent surfaces. This process will ensure proper adhesion of **VIP SATIN EMULSION**.
- **Subsequent coat** : Not required

SAFETY

- **VIP SATIN EMULSION** can be safely used in rooms that will be occupied the following day or where food stuff are stored or processed.
- Wear adequate protective equipment during application, remove splashes from skin with soap and water. In case of contact with eyes, rinse with ample water and seek medical advice if necessary.
- Ensure good ventilation during application and drying.
- Keep containers tightly closed and away from children.

MAINTENANCE

Surfaces prepared and painted according to specification will provide lasting protection and will facilitate maintenance. Carry out repairs as and when required and wash the surface occasionally; use mild detergent and light scrubbing to remove stains.

These recommendations are meant as a guide, no guarantee is implied since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

Manufactured and Distributed by:
Mauvilac Industries Ltd
 Pailles Road, Pailles, Republic of Mauritius
 Tel: (230) 206 4700
 Fax: (230) 286 5315

Jan 2004